



RC SUPER BOND

RUSH COAT FOR USE ON SMOOTH & CONCRETE SUBSTRATE A DRY PRE-MIXED POLYMER MODIFIED SAND CEMENT BOND COAT USED TO PROVIDE A MECHANICAL KEY FOR CEMENT AND GYPSUM PLASTER

Description

RC Super Bond Rush coat is a dry pre-mixed polymer modified sand cement bond coat used to provide a mechanical key for cement and gypsum plaster. The use of this product eliminates the need for hacking or chipping of the concrete surface before application of the plaster.

Advantages

- Single component
- Specially developed for hot weather
- High bond strength
- Polymer modified
- Non-toxic
- Interior & Exterior applications

Uses

For smooth concrete surfaces, especially where micro silica or GGBS is used, AAC blocks and other smooth substrates.

Physical Properties*

PROPERTY	TYPICAL RESULTS
Compressive strength	>18 MPa at 28 days
Flexural strength	>5.5 MPa at 28 days
*The above properties are average laboratory values	

Specification compliance

ASTM C 579:2001 Method B
BS 4551:1980

Packing

RC Super Bond is available in 50kg bags.

Coverage

Theoretical coverage rate for one bag of 50 kg would be 11 to 13 m² at 2-3mm thick

Shelf Life

12 months when stored in factory packed unopened bag, stored in a cool dry and elevated place away from direct sunlight.

Installation Guidelines

We provide detailed method statements on all products for use in various applications. These must be referred to prior to starting the work. The information below is a summary intended for guidance only.

Surface Preparation

Concrete substrate must be structurally sound. Loose or unsound concrete should be removed. Surfaces must be entirely free of oil, grease, paint, corrosion deposits, dust, laitance or other surface deposits. The substrate must be prepared to create a 'key' for bonding.

The substrate must be primed using clean water to achieve a saturated surface dry prior to application.

Mixing

RC Super Bond is supplied as a single component cementitious product in 50 kg bags. Pour 9.5 to 10.0 liter of clean water into suitable clean container and slowly add the product while mixing with low speed drill (300-500 rpm) with mixing paddle. Mix approximately for 3-5 minutes to achieve right smooth consistency.

Do not over mix or add additional water.

Application

Spray on to the substrate using a "Tyrolean" splatter box or with a hopper spray. Do not apply by trowel. Apply in two coats wet on wet but allow the first coat to stiffen before going over with the second coat.

Ensure that the entire area is coated and has a rough texture to act as a while mechanical key. Ensure that the product applied is still workable. Working time is typically 45 minutes at 30°C.

Curing

Immediately after application cure continuously with clean water in accordance with good concrete practice for three days.

Precautions

Do not add additional water or re-temper the mix.

Cure only with clean water, do not use any curing compound.

Ensure the temperature of the mortar does not exceed 35°C at the time of mixing.
Do not mix by hand.
Do not apply by trowel.
Do not part mix, use full bag.
Do not apply in rain or wet conditions or at temperature below 5°C.
Do not expose to running water until the product is fully cured for 7 days.

Technical Support

We offer full technical support package to specifiers, contractors and end users, as well as technical assistance on site and after sales consultations.

Health & Safety

As with all chemical products, caution should always be exercised. Protective clothing, such as gloves and goggles, should be worn. See packaging/MSDS for specific instructions.

Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately.

GUARANTEE

The information contained in this leaflet is based on our experience and technical knowledge, obtained through laboratory testing and from bibliographic material. Any use of this data beyond the purposes expressly specified in the leaflet will not be the Company's responsibility unless authorised by us. We shall not accept responsibility exceeding the value of the purchased product. The data shown on consumptions, measurement and yields are for guidance only and based on our experience. These data are subject to variation due to the specific atmospheric and jobsite conditions so reasonable variations from the data may be experienced. In order to know the real data, a test on the jobsite must be done, and it will be carried out under the client responsibility. We shall not accept responsibility exceeding the value of the purchased product. For any other doubt, consult our Technical Department. This version of bulletin replaces the previous one.

Reproduction, manipulation by computer, and transmission in whole or in part in any form or by any means (electronically, mechanically, by photocopying, recording, or otherwise) without the prior written consent of the copyright owner are prohibited.

Manufactured Exclusively for:

All Aspects Insulation Materials, P.O.Box: 39613, Sharjah, UAE, T: +971 6 5569913, F: +971 6 5569914

E: info@allaspects-emirates.com, W: www.allaspects.ae