



CONPLAST 40

SINGLE COMPONENT CEMENTITIOUS PLASTER SPECIALLY FORMULATED FROM SELECTED CEMENTS, SAND, ADMIXTURES AND AGGREGATES

Description

ConPlast 40 is a single component cementitious plaster specially formulated from selected cements, sand, admixtures and aggregates. Plastering application for use on all kinds of internal & external building surfaces.

Advantages

- Single component
- Specially developed for hot weather
- Non-toxic
- Interior & Exterior applications
- Machine or hand applied

Uses

Internal & external plaster for walls, ceilings & all types of block works

Physical Properties*

PROPERTY	TYPICAL RESULTS
Toxicity	Non-toxic
Aggregate size	2mm maximum
Fire resistance	Class 0 – BS 476, Part 6

*The above properties are average laboratory values

Specification Compliance

ASTM C 387
BS 5262:4551

Packing

ConPlast 40 is available in 50 kg bags.

Coverage

Theoretical coverage rate for one bag of 50 kg would be 2.00 m² at 15mm thick

Shelf Life

12 months when stored in factory packed unopened bag, stored in a cool dry and elevated place away from direct sunlight.

Application Properties

PROPERTY	TYPICAL RESULTS
Application temperature	5°C to 40°C
Minimum thickness	12mm
Maximum thickness	40mm in multiple layers of 20mm
Maximum temp. of mixed product	30°C
Application time	30 minutes at 20°C 15 minutes at 35°C
Water ratio	8.5 to 9.0 liter of clean water per 50 kg

Installation Guidelines

We provide detailed method statements on its products for use in various applications. These must be referred to prior to starting the work. The information below is a summary intended for guidance only.

Surface Preparation

Substrates must be structurally sound. Loose or unsound substrate should be removed. Surfaces must be entirely free of oil, grease, paint, corrosion deposits, dust, laitance or other surface deposits. The substrate must be prepared to create a 'key' for bonding.

The substrate must be primed using clean water to achieve a saturated surface dry prior to application.

Protection of reinforcement steel bars

Remove all corrosion deposits from the exposed reinforcement steel bars.

For protection against corrosion, coat the reinforcement steel bars with **Tek-Prime ZR**.

Priming

The substrate must be primed using clean water prior to application.

Rush coat application on concrete and smooth surfaces

Apply **RC Super Bond** on to the substrate using a “Tyrolean” splatter box or with a hopper spray. Do not apply by trowel. Apply in two coats wet on wet but allow the first coat to start setting before going over with the second coat. Ensure that the entire area is coated and has a rough texture to act as a mechanical key. Ensure that the product applied is still workable. Working time is typically 45 minutes at 30°C. For further details, please refer material technical data sheet.

Mixing

ConPlast 40 is supplied as a single component cementitious product in 50 kg bags. Pour 8.5 to 9.0 liter of clean water into suitable clean container and slowly add the product while mixing with low a speed drill (300-500 rpm) and a mixing paddle. Mix approximately for 3-5 minutes to achieve the right smooth consistency. Do not over mix or add additional water. Do not over mix or add additional water.

Application

The mixed material should be applied immediately. Apply the mixed product manually or by spraying method to the required thickness; wait until the applied material partially starts setting, then finish using a trowel to achieve a leveled dense surface. Do not use water to finish the surface.

Curing

Curing of **ConPlast 40** is essential and should begin by mist spraying the hardened **ConPlast 40** surface with clean potable water and maintain the dampness for 72 hours minimum for full cure. Alternatively if conditions do not allow the above method of curing, a curing liquid should be brush or spray applied to all plastered surfaces.

Precautions

Do not add additional water or re-temper the mix. Ensure the temperature of the mortar does not exceed 35°C at the time of mixing. Do not mix by hand. Do not part mix, use full bag. Do not apply in rain or wet conditions or at temperature below 5°C. Do not expose to running water until the product is fully cured for 7 days.

Technical Support

We offer full technical support package to specifiers, contractors and end users, as well as technical assistance on site and after sales consultations.

Health & Safety

As with all chemical products, caution should always be exercised. Protective clothing, such as gloves and goggles, should be worn. See packaging/MSDS for specific instructions.

Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately.

GUARANTEE

The information contained in this leaflet is based on our experience and technical knowledge, obtained through laboratory testing and from bibliographic material. Any use of this data beyond the purposes expressly specified in the leaflet will not be the Company's responsibility unless authorised by us. We shall not accept responsibility exceeding the value of the purchased product. The data shown on consumptions, measurement and yields are for guidance only and based on our experience. These data are subject to variation due to the specific atmospheric and jobsite conditions so reasonable variations from the data may be experienced. In order to know the real data, a test on the jobsite must be done, and it will be carried out under the client responsibility. We shall not accept responsibility exceeding the value of the purchased product. For any other doubt, consult our Technical Department. This version of bulletin replaces the previous one.

Reproduction, manipulation by computer, and transmission in whole or in part in any form or by any means (electronically, mechanically, by photocopying, recording, or otherwise) without the prior written consent of the copyright owner are prohibited.

Manufactured Exclusively for:

All Aspects Insulation Materials, P.O.Box: 39613, Sharjah, UAE, T: +971 6 5569913, F: +971 6 5569914

E: info@allaspects-emirates.com, W: www.allaspects.ae